

2019-6367  
2019-12-17

**TRI-LUX II Antifouling Series**

SUSPENSION

DOMESTIC

IMPORTANT

READ THE LABEL BEFORE USING.

KEEP OUT OF REACH OF CHILDREN. FOR USE ON BOATS ONLY.

SKIN AND EYE IRRITANT. NOT FOR SPRAY USE.  
ONLY BRUSH OR ROLLER APPLICATION.

ACTIVE INGREDIENT: Copper present as cuprous thiocyanate 11.88%  
WARNING, CONTAINS THE ALLERGEN – SOY.

REGISTRATION NO. 25544 PEST CONTROL PRODUCTS ACT.

DANGER

POISON

FLAMMABLE

NET CONTENTS 3.78 L

International Paint LLC  
6001 Antoine Drive  
Houston, RX 77091  
USA  
1 713 682-1711

2019-6367  
2019-12-17

**DISCLAIMER:**

The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application.

IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

**PRECAUTIONS:**

**KEEP OUT OF REACH OF CHILDREN.**

Keep away from heat, sparks and flame. Vapors heavier than air cause health and explosion hazards. Keep containers tightly closed when not in use. Avoid contact with eyes, skin and clothing. Do not breathe vapours. Wear chemical resistant gloves, goggles and footwear, and chemical resistant clothing including hood or hat at all times during handling and application. Use appropriate respiratory protection (e.g. dust mask) when removing old antifouling coatings.

Handle with care and mix carefully – When using, do not eat, drink or smoke – Take a shower immediately after work – Wear freshly laundered clothes daily – Wash hands and face before eating, drinking, smoking and using the toilet – Store and wash all protective clothing separately from household laundry – Wash protective clothing in detergent and hot water before reuse – Use only in well ventilated areas.

**FIRST AID:**

If swallowed:

Call a poison control centre or doctor immediately for treatment advice. Do not induce vomiting unless told to do so by a poison control centre or doctor. Do not give any liquid to the person. Do not give anything by mouth to an unconscious person.

If on skin or clothing:

Take off contaminated clothing. Rinse skin immediately with plenty of water for 15-20 minutes. Call a poison control centre or doctor for treatment advice.

If inhaled:

Move person to fresh air. If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably by mouth-to-mouth, if possible. Call a poison control centre or doctor for further treatment advice.

If in eyes:

Hold eye open and rinse slowly and gently with water for 15-20 minutes. Remove contact lenses,

2019-6367  
2019-12-17

if present, after the first 5 minutes, then continue rinsing eye. Call a poison control centre or doctor for treatment advice.

Take container, label or product name and Pest Control Product Registration Number with you when seeking medical attention.

**TOXICOLOGICAL INFORMATION:**

Treat symptomatically. This product contains petroleum distillates. Vomiting may cause aspiration pneumonia. Ingestion (drinking) of this product could cause serious injury or death. There is no antidote for solvent ingestion.

**ENVIRONMENTAL PRECAUTIONS:**

Toxic to aquatic organisms . This product contains petroleum distillate which is moderately to highly toxic to aquatic organisms. Avoid contamination of aquatic systems during application. Do not contaminate these systems through direct application, disposal of waste or cleaning of equipment.

**STORAGE:**

Prevent contamination. Store this product away from food or feed.

**DISPOSAL:**

DO NOT reuse the empty containers. Dispose in household garbage. Unused or partially used products should be disposed at provincially or municipally designated hazardous waste disposal sites.

**DIRECTIONS FOR USE**

TRI-LUX® II Antifouling Series

**PRODUCT DESCRIPTION:** TRI-LUX® II Antifouling Series is a unique copolymer bottom paint, available in a wide range of bright colors. Although specifically formulated for aluminum crafts and related surfaces, TRI-LUX® II Antifouling Series is equally compatible with fiberglass, wood, steel and lead. TRI-LUX® II Antifouling Series is ideal for aluminum outdrive and outboard motor lower units; provided the application instructions are followed. TRI-LUX® II Antifouling Series can be used in fresh, salt and brackish water.

**SURFACE PREPARATION:** Surface must be clean and dry and properly prepared prior to painting. All sanded surfaces must be wiped clean with INTERLUX® SPECIAL THINNER 216 to remove all sanding residue.

**GENERAL APPLICATION:** For use on primed aluminum, fiberglass, wood, steel and lead below the true waterline. Apply at least two full coats with a solvent resistant roller or pure bristle brush.

**MIXING AND THINNING:** Shake or mix and stir continuously while using. When brushing or rolling, do not thin this bottom paint – except for the first coat on bare wood with INTERLUX® SPECIAL THINNER 216.

2019-6367  
2019-12-17

**THEORETICAL COVERAGE:** Depending on surface condition, one litre of TRI-LUX® II Antifouling Series will usually cover 9.80 square metres, when rolled or brush applied.

**CLEAN-UP:** Use INTERLUX® SPECIAL THINNER 216 for cleaning paint brushes and equipment.

**ESTIMATED DRY TIMES:** TRI-LUX® II Antifouling Series may be overcoated with itself after 12 hours. Prior to launch, allow to dry for 12 hours, but no more than 90 days.

### **APPLICATION SYSTEMS**

**BARE ALUMINUM:** On small craft where sandblasting is not practical, i.e. aluminum pontoon boats, car top boats, etc., wipe bare metal with INTERLUX® SPECIAL THINNER 216 to remove oil and grease. Uniformly, sand surface to a bright finish with medium grit emery cloth. Wipe surface clean of dust with INTERLUX® SPECIAL THINNER 216. Immediately apply one thin coat of INTERLUX® VINYL-LUX® PRIMEWASH 353/354 thinned 25% with INTERLUX® VINYL-LUX® SOLVENT 355. Allow to dry a minimum of one hour but no more than twenty-four hours; then apply INTERLUX® INTERPROTECT® 2000E/2001E. Apply enough INTERLUX® INTERPROTECT® 2000E/2001E to obtain a 10 mil dry film thickness. This usually takes 4-5 coats to obtain this thickness, although the amount of paint is more important than the number of coats. Be sure to follow dry times on the INTERLUX® INTERPROTECT® 2000E/2001E label. When complete, apply at least 3 coats of TRI-LUX® II Antifouling Series. If dry times for INTERLUX® INTERPROTECT® 2000E/2001E cannot be followed, use the following alternate system. Apply four coats of INTERLUX® UNDERWATER METAL PRIMER 360R over the INTERLUX® VINYL-LUX® PRIMEWASH 353/354. On rivets and adjacent areas, apply a minimum of 5 coats of INTERLUX® UNDERWATER METAL PRIMER 360R. Finish with at least three coats of TRI-LUX® II Antifouling Series.

**ALUMINUM – PREVIOUSLY PAINTED WITH ANTIFOULING PAINT:** Remove incompatible antifouling paint (soft, tin-based copolymers or cuprous oxide based) and primer (EPOXY PRIMER MAY BE LEFT ON IF IT IS IN GOOD CONDITION) to bare aluminum and proceed with bare system above. If the surface was previously painted with TRI-LUX® II Antifouling Series paint and primer system is in good condition, sand with 80 grit sandpaper. Wipe off sanding residue with INTERLUX® SPECIAL THINNER 216. Any areas where the bare aluminum is exposed must be re-sanded with medium grit emery cloth and wiped clean. Immediately apply INTERLUX® UNDERWATER METAL PRIMER 360R to bare areas. Then apply at least two full coats of INTERLUX® UNDERWATER METAL PRIMER 360R to the entire underwater surface. Do not apply INTERLUX® UNDERWATER METAL PRIMER 360R or TRI-LUX® II Antifouling Series above the true waterline. Apply three coats of TRI-LUX® II Antifouling Series.

**ALUMINUM – PREVIOUSLY PAINTED WITH A FACTORY FINISH:** Wipe surface clean with INTERLUX® SPECIAL THINNER 216 to remove contaminants. Sand the surface with 120-grit sandpaper. Wipe the surface again with INTERLUX® SPECIAL THINNER 216, to remove sanding residue. Immediately spot prime any bare areas with INTERLUX® UNDERWATER METAL PRIMER 360R. Apply at least two full coats of INTERLUX®

2019-6367  
2019-12-17

UNDERWATER METAL PRIMER 360R (three coats to riveted areas), to the entire bottom, allowing appropriate dry times. After an overnight dry, apply at least three coats of TRI-LUX® II Antifouling Series. Do not apply INTERLUX® UNDERWATER METAL PRIMER 360R or TRI-LUX® II Antifouling Series above the true waterline.

UNDERWATER METALS INCLUDING SHAFTS, PROPELLERS, TRIM TABS, STRUTS AND THRU-HULL FITTINGS: These areas require special attention to initial surface preparation in order to improve adhesion. Treat these areas the same as bare aluminum. The longevity of this system will probably not be equal to that of the remainder of the boat due to the R.P.M.s these parts withstand. For more details contact Interlux Technical Service at 1-800-468-7589.

BARE FIBERGLASS – NO SAND SYSTEM: Clean entire surface thoroughly with INTERLUX® FIBERGLASS SOLVENT WASH 202, changing rags frequently. Before the liquid dries, wipe clean with dry cloth. Be sure all wax and other contaminants are removed; if surface is not clean, delamination will occur. Apply one thin, continuous coat of INTERLUX® AL 200 FIBERGLASS PRIMER® with brush or roller. Do not spray or sand. Allow to dry two hours, but no more than three hours, and apply the first coat of TRI-LUX® II Antifouling Series. Apply a minimum of three coats of TRI-LUX® II Antifouling Series.

BARE FIBERGLASS – SANDING SYSTEM: Be sure all wax and other contaminants are removed by cleaning the surface with INTERLUX® FIBERGLASS SOLVENT WASH 202. Wash the surface thoroughly with a rag that has been soaked in INTERLUX® FIBERGLASS SOLVENT WASH 202 and, before the liquid dries, wipe off with a clean dry cloth. Change the rags frequently. After the surface has been cleaned, sand with 80 grit sandpaper until a flat, matte finish has been obtained. Wipe off the sanding residue with INTERLUX® FIBERGLASS SOLVENT WASH 202. Apply three coats of TRI-LUX® II Antifouling Series.

BARE WOOD: Sand entire surface thoroughly to a smooth finish with 80 grit sandpaper. Clean off the sanding residue using a rag that has been dampened with INTERLUX® SPECIAL THINNER 216. Apply the first coat of TRI-LUX® II Antifouling Series reduced with INTERLUX® SPECIAL THINNER 216 (10% maximum) to penetrate the porous grain. Fill seams with INTERLUX® SEAM COMPOUND 30. Apply second and third coats of TRI-LUX® II Antifouling Series unreduced.

PREVIOUSLY PAINTED FIBERGLASS AND WOOD – GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface with 80 grit sandpaper. Wipe surface clean. Apply three coats of TRI-LUX® II Antifouling Series.

Prevent paint chips or dust caused by removing paint from entering water. DO NOT place the painted parts in water after painting until the paint is fully cured (see dry times on the label).

NOTE: TRI-LUX® II Antifouling Series white may show a green patina at the waterline, especially when applied in thin coats. This patina does not affect antifouling performance. This product has been shown to be efficacious as an antifouling coating for a period of at least two years, when proper film thickness is applied.

2019-6367  
2019-12-17

Interlux, for more information call 1 713 682-1711,  
or write 6001 Antoine Drive, Houston TX 77091, USA

**NOTICE TO USER**

This pest control product is to be used only in accordance with the directions on the label. It is an offence under the *Pest Control Products Act* to use this product in a way that is inconsistent with the directions on the label.

NOT REGISTERED FOR USE IN THE UNITED STATES OF AMERICA