

2017-0253
2017-09-20

FIBERGLASS BOTTOMKOTE HIGH SOLIDS SERIES

ANTIFOULING PAINT

DOMESTIC

SOLUTION

KEEP OUT OF REACH OF CHILDREN

IMPORTANT

READ THE LABEL BEFORE USING. FOR
USE ON BOATS ONLY.

SKIN AND EYE IRRITANT. NOT
FOR SPRAY USE.

ONLY BRUSH OR ROLLER APPLICATION.

GUARANTEE: CUPROUS OXIDE 42.67% COPPER
(AS ELEMENTAL) 37.90% REGISTRATION NO.
24392

PEST CONTROL PRODUCTS ACT

3.78 L

(Red, Green, Blue, Grey White, Midnight Grey, Black, Brown) CAUTION
FLAMMABLE
DANGER POISON

International Paint LLC, 6001 Antoine Drive, Houston, Texas 77091 USA
713-682-1711

2017-0253
2017-09-20

FIBERGLASS BOTTOMKOTE HIGH SOLIDS SERIES A Modified Epoxy Antifouling Paint

DIRECTIONS FOR USE:

PRODUCT DESCRIPTION: FIBERGLASS BOTTOMKOTE HIGH SOLIDS SERIES provides excellent, long term antifouling protection against marine growth. Its modified epoxy base renders a hard, smooth finish with outstanding durability and abrasion resistance. It has universal application over all types of properly prepared bottom paints and surfaces (except aluminum). Ideal for use on fast fiberglass boats, as well as wood and steel hulls, when a tougher than normal coating is desired. May be burnished even smoother for racing sail and power boats.

SURFACE PREPARATION: Surface must always be clean, dry and properly prepared prior to painting. Failure to do so will lead to eventual blistering and/or peeling. All sanded surfaces must be wiped clean with INTERLUX SPECIAL THINNER 216 to remove sanding residue.

GENERAL APPLICATION: For use on boats below the true waterline. Can be brushed or rolled on fiberglass, wood, steel and previously painted surfaces per application systems below. Do not use on aluminum. Two (2) coats are recommended for best performance.
MIXING & THINNING: Shake or mix thoroughly and stir continuously while using. When applying with brush or roller, do not thin bottom paints.

THEORETICAL COVERAGE: Depending on surface and conditions, one litre of bottom paint will usually cover 8.58 square metres of surface when brushed or rolled.
CLEAN-UP: Use INTERLUX SPECIAL THINNER 216 for cleaning equipment and paint brushes.

ESTIMATED DRY TIMES: INTERLUX bottom paints are designed for overcoating after an overnight dry. Prior to launching, allow a minimum dry of overnight and maximum of 60 days. If drying conditions are poor, or if paint was applied too thickly, longer periods of drying will be required. Fresh coats of paint must be thoroughly dry before overcoating.

APPLICATION SYSTEMS

PREVIOUSLY PAINTED SURFACES - Good Condition: Remove all traces of loose paint and contamination by sanding the entire surface well with 80-120 grit production sandpaper; wipe surface clean. Apply 2 coats of bottom paint.

Poor Condition: Completely remove all old paint with INTERLUX PINTOFF 299 for fiberglass, INTERLUX PINTOFF 199 for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS – No Sand System:

Wash entire surface thoroughly with INTERLUX FIBERGLASS SOLVENT WASH 202 changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed.) Repair imperfections with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Apply one thin continuous coat of INTERLUX AL200 FIBERGLASS PRIMER with brush

2017-0253

2017-09-20

or roller. Do not spray; do not sand. Allow to cure between 2-3 hours - no more, no less. Apply 2 coats of bottom paint.

BARE FIBERGLASS – Sanding System: Wash entire surface thoroughly with INTERLUX FIBERGLASS SOLVENT WASH 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed.) Repair imperfections with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Sand entire gelcoat well with 80-120 grit production sandpaper until a flat, matte finish is obtained; wipe surface clean. Apply 2 coats of bottom paint.

BARE WOOD: Sand entire surface thoroughly to a smooth finish with 80 grit production sandpaper; wipe surface clean. Repair imperfections with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Apply first coat of bottom paint reduced with INTERLUX SPECIAL THINNER 216 (10% maximum) to penetrate the porous grain. Fair seams with INTERLUX SEAM COMPOUND 30. Apply second and third coats of bottom paint unreduced.

***BARE STEEL:** Sandblast surface to a near white metal; remove blast residue with a broom and air hose. Immediately apply one very thin coat of Interlux Viny-Lux 353/354; allow to dry minimum of one hour, maximum of 24. Do not sand. Fill in all imperfections with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand smooth and wipe clean. Apply 3 coats of INTERLUX UNDERWATER METAL PRIMER 360R; followed by two coats of bottom paint.

* This is a simple system for small areas. For a more advanced, professional system, please consult the INTERLUX Technical Service Department, International Paint Inc., P.O. Box 386, Union, NJ 07083.

DO NOT place the painted parts in water after painting until the paint is fully cured (see recommended times on the label). It is recommended that you prevent paint chips or dust caused by removing paint from entering water.

NOTICE TO USER: This control product is to be used only in accordance with the directions on the label. It is an offense under the *Pest Control Products Act* to use this product in a way that is inconsistent with the directions on the label. The user assumes the risk to persons or property that arises from any such use of this product.

ENVIRONMENTAL HAZARDS: Toxic to aquatic organisms. Do not contaminate water by spillage, cleaning of equipment or disposal of wastes. Do not allow chips or dust generated during paint removal to enter water.

DISPOSAL: Do not reuse container for any other purpose. Dispose of empty container and paint debris in accordance with provincial requirements. For information on the disposal of unused, unwanted product, and the clean-up of spills, contact the manufacturer or the Provincial Regulatory Agency.

2017-0253
2017-09-20

PRECAUTIONS: Keep away from heat, sparks and flame. Vapours heavier than air cause health and explosion hazards. Keep containers tightly closed when not in use. Avoid contact with eyes, skin and clothing. Do not breathe vapours. Wear chemical resistant gloves, goggles and footwear, and chemical resistant clothing including hood or hat at all times during handling and application.

- KEEP OUT OF REACH OF CHILDREN - Handle with care and mix carefully - When using, do not eat, drink or smoke - Take a shower immediately after work - Wear freshly laundered clothes daily - Wash hands before eating, drinking, chewing gum, using tobacco or using the toilet - Store and wash all protective clothing separately from household laundry - Wash protective clothing in detergent and hot water before reuse - Use only in well ventilated areas.

FIRST AID: IF IN EYES: Hold eye open and rinse slowly and gently with water for 15-20 minutes. Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye. Call a poison control centre or doctor for treatment advice. IF ON SKIN OR CLOTHING: Take off contaminated clothing. Rinse skin immediately with plenty of water for 15-20 minutes. Call a poison control centre or doctor for treatment advice. IF INHALED: Move person to fresh air. If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably by mouth-to-mouth, if possible. Call a poison control centre or doctor for further treatment advice. IF SWALLOWED: Call a poison control centre or doctor immediately for treatment advice. Have a person sip a glass of water if able to swallow. Do not induce vomiting unless told to do so by a poison control centre or doctor. Do not give anything by mouth to an unconscious person. Take container, label or product name and Pest Control Product Registration Number with you when seeking medical attention.

TOXICOLOGICAL INFORMATION: Ingestion (drinking) of this product could cause serious injury or death. There is no antidote for solvent ingestion. Treat symptomatically.

EPA EST. NO. 2693-NJ-1

NOT REGISTERED FOR USE IN THE UNITED STATES OF AMERICA