

2017-1190
2017-10-19

MICRON CSC EXTRA (VARIOUS COLOURS)
ANTIFOULING PAINT

DOMESTIC

SUSPENSION

KEEP OUT OF REACH OF CHILDREN

IMPORTANT

READ THE LABEL BEFORE USING.

FOR USE ON BOATS ONLY.

SKIN AND EYE IRRITANT.

NOT FOR SPRAY USE.

GUARANTEE: CUPROUS OXIDE 37.04%

COPPER (AS ELEMENTAL) 32.90%

REGISTRATION NO. 24393

PEST CONTROL PRODUCTS ACT.

NET CONTENTS: 3.78 L

(Blue, Red, Green, Black, Shark White, Brown)

CAUTION

FLAMMABLE

DANGER

POISON

International Paint LLC,
6001 Antoine Drive, Houston, Texas 77091 USA
713-682-1711

Micron CSC Extra Antifouling paint

PRODUCT DESCRIPTION:

MICRON CSC EXTRA™ is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting.

MICRON CSC EXTRA™ contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling, MICRON CSC EXTRA™ can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

DIRECTIONS FOR USE:

COMPATIBILITY: MICRON CSC EXTRA™ can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. MICRON CSC EXTRA™ should not be applied over MICRON 33, MICRON 44 or soft antifouling paints. These old coatings should be removed. MICRON CSC EXTRA™ is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter as supplied

THINNER: Brushing – BRUSH EASE 433

Spraying – SPECIAL THINNER 216

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: SPECIAL THINNER 216 or BRUSH EASE 433

THEORETICAL COVERAGE: 10.8 square meters/liter will yield 2 mils dry film thickness

DRY TIMES: Touch dry 2 hours

(25°C) Dry to overcoat – 16 hours minimum*

Dry to launch – 16 hours minimum*

APPLICATION TEMPERATURE: 10°C and above (Air and hull)

*If the air temperature falls below 10°C (50°F) during the dry time extend the dry times by 12 hours minimum.

APPLICATION SYSTEMS

Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of MICRON CSC EXTRA™ by brush or solvent resistant 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use INTERLUX BRUSH EASE 433 to improve handling. Certain areas of hull experience faster polishing than other areas.

These areas include the waterline, the leading edge of the keel and rudder, the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that MICRON CSC EXTRA™ does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION:

Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet-or-dry sandpaper; wipe surface clean with Interlux Special Thinner 216. Apply at least 2 coats of MICRON CSC EXTRA™ allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION:

Completely remove all old antifouling paint with INTERLUX FIBERGLASS PINTOFF 299 for fiberglass, INTERLUX PINTOFF 199 for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM:

Wash entire surface thoroughly with INTERLUX FIBERGLASS SOLVENT WASH 202 changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed.) Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Apply one thin continuous coat of INTERLUX AL200 FIBERGLASS PRIMER with brush or roller. Do not spray; do not sand. Allow to cure between 2 hours but no more than 3 hours. Apply first coat of MICRON CSC EXTRA™ and allow to dry overnight. Apply at least one more coat of MICRON CSC EXTRA™ allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM:

Wash entire surface thoroughly with INTERLUX FIBERGLASS SOLVENT WASH 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed.) Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with INTERLUX FIBERGLASS SOLVENT WASH 202. Apply two or more coats of MICRON CSC EXTRA™ allowing proper dry times.

BARE WOOD:

Sand entire surface thoroughly with 80-grit production sandpaper; wipe surface clean with INTERLUX BRUSH EASE 433. Repair imperfections with INTERLUX EPOXY SURFACING & FAIRING COMPOUND 417A/418B; sand and wipe clean. Apply first coat of MICRON CSC EXTRA™ reduced with INTERLUX BRUSH EASE 433 (10% maximum). Fill seams with INTERLUX SEAM COMPOUND 30 between first and second coats of MICRON CSC EXTRA™.

UNDERWATER METALS:

Contact the INTERLUX Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC EXTRA™ SHARK WHITE may change color at the waterline.

DO NOT place the painted parts in water after painting until the paint is fully cured (see recommended times on the label). It is recommended that you prevent paint chips or dust caused by removing paint from entering water.

NOTICE TO USER: This control product is to be used only in accordance with the directions on the label. It is an offense under the *Pest Control Products Act* to use this product in a way that is inconsistent with the directions on the label. The user assumes the risk to persons or property that arises from any such use of this product.

ENVIRONMENTAL HAZARDS: Toxic to aquatic organisms. Do not contaminate water by spillage, cleaning of equipment or disposal of wastes. Do not allow chips or dust generated during paint removal to enter water.

DISPOSAL: Do not re-use container for any purpose. Dispose of empty container and paint debris in accordance with provincial requirements. For information on the disposal of unused, unwanted product, and the clean-up of spills, contact the manufacturer or the Provincial Regulatory Agency.

PRECAUTIONS: Keep away from heat, sparks and flame. Vapours heavier than air cause health and explosion hazards. Keep containers tightly closed when not in use. Avoid contact with eyes, skin and clothing. Do not breathe vapours. Wear chemical resistant gloves, goggles and footwear, and chemical resistant clothing including hood or hat at all times during handling and application.

- KEEP OUT OF REACH OF CHILDREN - Handle with care and mix carefully -
When using, do not eat, drink or smoke - Take a shower immediately after work - Wear freshly laundered clothes daily - Wash hands before eating, drinking, chewing gum, using tobacco or using the toilet - Store and wash all protective clothing separately from household laundry - Wash protective clothing in detergent and hot water before reuse -
Use only in well ventilated areas.

FIRST AID: IF IN EYES: Hold eye open and rinse slowly and gently with water for 15-20 minutes. Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye. Call a poison control centre or doctor for treatment advice. IF ON SKIN OR CLOTHING: Take off contaminated clothing. Rinse skin immediately with plenty of water for 15-20 minutes. Call a poison control centre or doctor for treatment advice. IF INHALED: Move person to fresh air. If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably by mouth-to-mouth, if possible. Call a poison control centre or doctor for further treatment advice. IF SWALLOWED: Call a poison control centre or doctor immediately for treatment advice. Have a person sip a glass of water if able to swallow. Do not induce vomiting unless told to do so by a poison control centre or doctor. Do not give anything by mouth to an unconscious person. Take container, label or product name and Pest Control Product Registration Number with you when seeking medical attention.

TOXICOLOGICAL INFORMATION: Ingestion (drinking) of this product could cause serious injury or death. There is no antidote for solvent ingestion. Treat symptomatically.

EPA EST. NO. 2693-NJ-1

NOT REGISTERED FOR USE IN THE UNITED STATES OF AMERICA